

UZIARNIENIE MIESZANKI MINERALNEJ

DROGI NR 653 odcinek Przebród - Suwałki od km 24 + 751 do km 28 + 798
warstwa ścieralna

lokalizacja km+hm	sito														
	0.075	0.150	0.180	0.300	0.420	0.800	2.000	4.000	6.300	8.000	10.000	12.000	16.000	20.000	25.000
24 + 800 L	8.3	10.9	12.0	16.0	19.5	27.4	41.9	66.6	73.1	78.1	86.2	96.3	100.0	100.0	100.0
25 + 250 L	7.6	9.3	9.8	12.4	14.8	22.2	37.0	66.1	77.1	83.6	91.1	97.2	100.0	100.0	100.0
25 + 500 P	10.2	11.9	12.5	14.9	16.9	23.6	36.6	64.2	73.8	81.0	91.1	98.3	100.0	100.0	100.0
26 + 250 L	9.2	11.5	12.8	18.2	21.8	30.4	42.4	60.9	73.4	79.7	88.7	95.8	100.0	100.0	100.0
26 + 750 L	8.3	10.9	12.0	16.0	19.4	27.3	41.9	66.6	73.1	78.1	86.2	96.3	100.0	100.0	100.0
27 + 500 P	11.9	15.7	17.2	22.2	30.1	43.4	58.2	70.5	79.5	84.0	90.1	96.8	100.0	100.0	100.0
28 + 250 L	10.0	13.2	14.7	22.9	29.8	43.6	52.9	60.8	75.3	82.2	90.1	97.4	100.0	100.0	100.0
28 + 750 L	10.3	13.3	15.0	24.3	31.3	44.8	54.0	61.2	74.9	82.0	88.2	95.4	100.0	100.0	100.0
średnia	9.5	12.0	13.0	17.9	22.4	33.5	47.0	64.8	75.6	81.8	90.0	97.1	100.0	100.0	100.0
granica dolna warstwa ścieralna	7.0	11.0	12.0	16.0	18.0	25.0	35.0	47.0	57.0	66.0	73.0	87.0	100.0	100.0	100.0
granica górna warstwa ścieralna	9.0	15.0	17.0	23.0	27.0	36.0	48.0	60.0	75.0	89.0	100.0	100.0	100.0	100.0	100.0

Marek Jerzy Szyszko
 KONTROLA LABORATORYJNA
 ROBÓT DROGOWYCH
 nr upr. DODP-55/94