

UZIARNIENIE MIESZANKI MINERALNEJ
DROGA NR 653 Olecko - Bakalarzewo - Suwałki m.PRZEBRÓD
WARSTWA III

lokalizacja km+hm	sito																
	0,075	0,150	0,180	0,300	0,420	0,800	2,000	4,000	6,300	8,000	10,000	12,000	16,000	20,000	25,000	31,500	38,100
23+800 P	2,8	3,8	4,5	8,3	12,1	27,2	38,3	46,2	54,1	59,7	68,5	75,4	91,8	100,0	100,0	100,0	100,0
24+350 L	3,4	4,6	4,9	7,8	10,6	23,0	34,7	43,8	51,1	54,6	57,8	69,8	96,2	100,0	100,0	100,0	100,0
24+850 P	3,3	5,0	6,2	12,2	17,2	33,3	48,5	60,4	74,4	85,7	90,8	100,0	100,0	100,0	100,0	100,0	100,0
średnia	3,7	5,1	5,9	10,6	14,7	29,7	42,5	52,2	61,6	68,3	74,8	83,2	97,0	100,0	100,0	100,0	100,0
granica dolna w. wiążąca 0/16	5,0	6,0	7,0	10,0	13,0	20,0	30,0	42,0	54,0	60,0	67,0	77,0	87,0	100,0	100,0	100,0	100,0
granica górna w. wiążąca 0/16	8,0	14,0	16,0	21,0	25,0	33,0	45,0	60,0	73,0	83,0	89,0	100,0	100,0	100,0	100,0	100,0	100,0
granica dolna podbudowa 0/25	4,0	5,0	5,0	6,0	7,0	12,0	19,0	27,0	36,0	42,0	48,0	57,0	66,0	76,0	87,0	100,0	100,0
granica górna podbudowa 0/25	7,0	11,0	12,0	15,0	18,0	24,0	35,0	47,0	58,0	65,0	71,0	81,0	90,0	100,0	100,0	100,0	100,0

**Krzywe uziarnienia mieszanki mineralnej dla poszczególnych próbek na tle
krzywych granicznych jak dla warstwy wiążącej 0/16 mm i warstwy
podbudowy 0/25mm KR 3-6 wg normy PN-S-96025;2000**

